

Tradical® Pont d'Adhérence

Keying primer for interior substrates

Characteristics of Tradical® Pont d'Adhérence

Density < 0.9 kg/dm³

Does not contain any VOCs or preservatives

Definition

Keying primer for interior storey-high panel substrates, old coatings, and heterogeneous substrates.

Identification

Tradical® Pont d'Adhérence is a ready-to-mix powder for manual application.

Areas of use

Tradical® Pont d'Adhérence is designed for indoor use to prepare vertical walls, ceilings, arches and between joists, before you apply Tradical® Décor.

→ ADMISSIBLE SUBSTRATES

Dry surfaces

Types of substrate

Gypsum plasterboard and cellulose board

Gypsum block partitioning walls

Hydraulic, gypsum, lime, and cement renders

Old acrylic paint, pre-sanded oil-based paint

Non-resilient thick plastic coatings (otherwise sanded)

Heterogeneous substrates

→ PREPARATION

Preparing the substrates

- Clean, sound, dust-free, according to the French Building Code
- Substrates contaminated by saltpetre should be treated (See Tradical® PZ technical data sheet)
- Any cracks must be rectified and dried before carrying out any work

Preparing the product:

Manual:

- Slowly mix for 3 to 4 minutes after adding 5.5 litres of water for each 5 kg bucket of Tradical® Pont d'Adhérence to achieve a thick, homogeneous consistency (for the 1.5 kg bucket, add 1.7 litres of water)
- Leave to stand for 5 minutes before applying
- Mix again briefly but regularly during application to ensure the product remains homogeneous
- Do not add anything else

Tools

Mixer, measurer, roller, and brush

→ APPLICATION

- Spread the Tradical® Pont d'Adhérence using the brush or roller. Repeat across to avoid missing any spots.

Usage:

Application	Yield per m ²	Yield per 5 kg bucket
1 coat	approx. 110 to 140 g	35 to 45 m ²

Tradical® Pont d'Adhérence includes:

Tradical® Interior Lime Render:

- Tradical® Décor
- Tradical® Finilys
- Tradical® Lait de Chaux
- Tradical® Premium
- Tradical® Pont d'Adhérence
- Tradical® Régulateur de Porosité



Lhoist Southern Europe
BCB

Adresse: ZAC de Valentin
rue du Choumois - BP 3011
25045 BESANÇON cedex
Tel. + 33 (0)3 81 47 40 10
Fax + 33 (0)3 81 47 40 19
contact@bcb-tradical.com
www.bcb-tradical.com

Tradical® Pont d'Adhérence

Keying primer for interior substrates

Sampling

Mix proportion	Tradical® Pont d'Adhérence	+ Water
Work site	1 bucket of 5 kg	+ 5.5 l
Equivalent sample for approx. 1 m ²	110 g or 120 ml	+ 120 ml

IMPORTANT

- Mix the amount of product required for each coating surface in one go
- Preservation of product once prepared: 24 to 48 hours
- Once completed, maintain substrate at room temperature for 3 to 4 days

Atmospheric conditions

Apply at a temperature of between +8 °C and +30 °C.

→ GENERAL INFORMATION

Qualifications

Only qualified persons with sound knowledge of interior renders or persons who have passed the CHAUX INTÉRIEUR module in the BCB training programme may use Tradical® Pont d'Adhérence.

See also

- Tradical® brochures and technical data sheets
- Relevant parts of the French Building Code

Packaging and storage

Tradical® Pont d'Adhérence comes in a 1.5 kg or 5 kg bag and can be stored for 1 year in its original packaging.

Guarantee

- Manufacturer's civil liability, SMABTP contract: ALPHA-BAT Fabricants no. 512806 E.
- Within the scope of the company's civil liability insurance

Tradical® Pont d'Adhérence includes:

Tradical® Interior Lime Render:

- Tradical® Décor
- Tradical® Finilys
- Tradical® Lait de Chaux
- Tradical® Premium
- Tradical® Pont d'Adhérence
- Tradical® Régulateur de Porosité



Lhoist Southern Europe
BCB

Adresse: ZAC de Valentin
rue du Choumois - BP 3011
25045 BESANÇON cedex
Tel. + 33 (0)3 81 47 40 10
Fax + 33 (0)3 81 47 40 19
contact@bcb-tradical.com
www.bcb-tradical.com



For further information visit our website
www.ozhemp.com.au
Email: info@ozhemp.com.au
Tel: 61 8 6424 8262 Fax: 61 8 6424 8782